

: 0129-4094247, 4094200

: www.steelstar.com



# **TEST CERTIFICATE**

No.

013041

Issue Date:

06.08.2009

Issued To : M/s SHIVALIK SILICA

Village Agawali, Tehsil Bayana,

District Bharatpur - 321401 (Raj.)

Sample Particulars :

SAMPLE OF SILICA STONE, MARKED AS C

#### STAR WIRE (INDIA) LTD. (DIAGNOSTIC CENTER)

21/4, MATHURA ROAD, BALLABGARH-121 004

TELEPHONE

4094280,2241263/64 : 0129-2241265, 2246765 FASCIMILLIE : swdc06@yahoo.co.in

E-MAIL

VISIT US AT

Date of sample Receipt

31.07.2009 31.07.2009

Sample drawn by

Request No./Date

Job order no.

CUSTOMER

233711

#### **TEST RESULTS**

DATE OF TESTING

01.08.2009 TO 04.08.2009

PROTOCOL USED

CHEMICAL COMPOSITION (% BY WT.)

TEST

SILICA (SiO<sub>2</sub>)

IRON OXIDE (Fe<sub>2</sub>O<sub>3</sub>)

ALUMINIUM OXIDE (Al2O3)

RESULTS

99.07

0.39

0.31


REMARKS :

**AUTHORISED SIGNATORY** 

Note 1. Sample will be retained only for one month.

2. The results listed refer only to the tested sample and applicable parameters. Endorsement of product is neither inferred nor implied.

3. Total liability of our works is limited to invoiced amount.





# **TEST CERTIFICATE**

Issue Date:

06.08.2009

Issued To: M/s SHIVALIK SILICA

Village Agawali, Tehsil Bayana,

Sample Particulars : District Bharatpur - 321401 (Raj.)

SAMPLE OF SILICA STONE, MARKED AS B

## STAR WIRE (INDIA) LTD. (DIAGNOSTIC CENTER)

21/4, MATHURA ROAD, BALLABGARH-121 004

TELEPHONE

**FASCIMILLIE** E-MAIL

VISIT US AT

Request No./Date Date of sample Receipt

Sample drawn by

Job order no.

: 0129-4094247, 4094200 4094280,2241263/64

: 0129-2241265, 2246765 : swdc06@yahoo.co.in : www.steelstar.com

31.07.2009 31.07.2009

CUSTOMER 233710

**TEST RESULTS** 

DATE OF TESTING

01\_08.2009 TO .04\_08.2009

PROTOCOL USED

CHEMICAL COMPOSITION (% BY WT.)

TEST

SILICA (SiO2)

IRON OXIDE (Fe<sub>2</sub>O<sub>3</sub>)

ALUMINIUM OXIDE (Al2O3)

RESULTS

98.97

0.39

0.31

\*\*\*\*\*\*\*


REMARKS :

**AUTHORISED SIGNATORY** 

Note 1. Sample will be retained only for one month.

2. The results listed refer only to the tested sample and applicable parameters. Endorsement of product is neither inferred nor implied.

3. Total liability of our works is limited to invoiced amount.





#### **TEST CERTIFICATE**

No.

013039

Issue Date:

06.08.2009

Issued To: M/s SHIVALIK SILICA

Village Agawali, Tehsil Bayana,

District Bharatpur - 321401 (Raj.)

Sample Particulars:

SAMPLE OF SILICA STONE, MARKED AS A

## STAR WIRE (INDIA) LTD. (DIAGNOSTIC CENTER)

21/4, MATHURA ROAD, BALLABGARH-121 004

TELEPHONE

**FASCIMILLIE** E-MAIL

**VISIT US AT** 

Request No./Date

Date of sample Receipt Sample drawn by

Job order no.

: 0129-4094247, 4094200 4094280,2241263/64

: 0129-2241265, 2246765 : swdc06@yahoo.co.in : www.steelstar.com

NIL

31.07.2009 31.07.2009

CUSTOMER 233709

**TEST RESULTS** 

DATE OF TESTING

01.08.2009 TO 04.08.2009

PROTOCOL USED

CHEMICAL COMPOSITION (% BY WT.)

TEST

SILICA (SiO<sub>2</sub>)

IRON OXIDE (Fe<sub>2</sub>O<sub>3</sub>)

ALUMINIUM OXIDE (Al2O3)

RESULTS

99.12

0.38

0.26

\*\*\*\*\*\*\*


REMARKS :

**AUTHORISED SIGNATORY** 

Note 1. Sample will be retained only for one month.

2. The results listed refer only to the tested sample and applicable parameters. Endorsement of product is neither inferred nor implied.

3. Total liability of our works is limited to invoiced amount.





# **TEST CERTIFICATE**

Issue Date:

06.08.2009

Issued To: M/s SHIVALIK SILICA Village Agawali, Tehsil Bayana,

District Bharatpur - 321401 (Raj.)

Sample Particulars:

SAMPLE OF SILICA SAND

# STAR WIRE (INDIA) LTD. (DIAGNOSTIC CENTER)

21/4, MATHURA ROAD, BALLABGARH-121 004

TELEPHONE

: 0129-4094247, 4094200 4094280,2241263/64

**FASCIMILLIE** 

: 0129-2241265, 2246765 : swdc06@yahoo.co.in

E-MAIL VISIT US AT : www.steelstar.com

Request No./Date

31.07.2009

Date of sample Receipt

: 31.07.2009

Sample drawn by

Job order no.

CUSTOMER

233708

## **TEST RESULTS**

DATE OF TESTING

01:08:2009 .....TO..04:08:2009 .....

PROTOCOL USED

CHEMICAL COMPOSITION (% BY WT.)

TEST

RESULTS

SILICA (SiO<sub>2</sub>)

98.12

IRON OXIDE (Fe<sub>2</sub>O<sub>3</sub>)

0.81

ALUMINIUM OXIDE (Al2O3)

0.65

\*\*\*\*\*\*\*

REMARKS :

Note 1. Sample will be retained only for one month.

2. The results listed refer only to the tested sample and applicable parameters. Endorsement of product is neither inferred nor implied.

3. Total liability of our works is limited to invoiced amount.